



TECHNICAL DATA

NEVILLE CHEMICAL COMPANY
2800 NEVILLE ROAD
PITTSBURGH, PA 15225-1496
(412) 331-4200

PB-100 Light Resin

10/00

PB-100 Light Resin		
Physical Properties	Typical Properties	Specifications
Softening Point, R&B°C (ASTM E-28)*	103	103 ± 5
Gardner Color (50% in 100 Solvent) (ASTM D-1544)*	14	17 Max.
Flash Point, °F (COC) (ASTM D-92)*	400	---
Specific Gravity @ 25°C (ASTM D-71)*	1.07	---
Iodine Number, Wijs (ASTM D-1959)*	140	---
Molecular Weight, No Avg., GPC (ASTM D-3536)*	445	---
Form	Flaked	---
* Referenced Test Method		

TSCA Status: Neville Chemical Company certifies that all components of this product are on the TSCA Inventory.

PACKAGING: PB-100 Light Resin is shipped flaked in 50-pound bags, 40 bags per pallet.

Due to storage conditions, warehousing practices and climate, flaked resins may remass (revert to a solid form). Because these variables cannot be controlled by Neville Chemical Company, no guarantee, either implicit or explicit, is made by the manufacturer.

The sale of Neville Chemical Company products is subject to the terms and conditions set forth in the contract, invoice, and/or bill of lading. No warranty is expressed or implied regarding: the use of these data or products, the results obtained from the use of these data or products, or the freedom from any patent infringement from the use of these data or products.

