

Technical Data Sheet

KNB 25H

Technical Name: Acrylonitrile-butadiene Rubber

CAS #: 9003-18-3
Appearance: Nitrile Bale

Technical Parameters:

our randinotoro.	IVIIN	IVIAX
VOL-MATTER		0.50%
ASH		0.80%
BOUND AN.	26.0%	30.0%
RAW MV (ML 1 + 4, 100 C)	73.0	87.0
TENSILE STRENGTH 40	200	
ELONGATION 40	300%	
300% MODULUS 40	150	210

May

The above information has been compiled from what we believe to be credible sources. To our knowledge the information is accurate and reliable, however, it is not guaranteed. Any recommendations issued by HB Chemical personnel or literature is derived from experience and by no means should be taken as fact or construed as a recommendation to violate of any law, regulation or patent. It is the users responsibility to determine the suitability of any HB supplied material in their application. The individual conditions of each customer are well outside of our control and we cannot be held liable for its functionality and use. Please contact our office should you need specific information beyond what is supplied above. As with all Chemical usage safety precautions beyond the stated are highly recommended.