



A Ravago Chemicals Company

Technical Data Sheet

NORDEL 3745P PRIME

Technical Name: HYDROCARBON RUBBER EPDM
CAS #: SEE BELOW
Appearance: TRANSLUCENT PELLETS

Technical Parameters:

	Min	Max
Mooney Viscosity	41	49
Ethylene Wt	68%	72%
ENB Wt	0.1%	1.0%
Volatiles Total Wt		0.4%
Gel Conc (200) < than 12 count, per 5.0 m2	Pass	
Yellowness Index		7

25038-36-2 >99.0
16219-75-3 <0.005

The quality of EPDM products may be affected by exposure to artificial or natural light. The product should be stored indoors in its original packaging and out of direct sunlight.

The above information has been compiled from what we believe to be credible sources. To our knowledge the information is accurate and reliable, however, it is not guaranteed. Any recommendations issued by HB Chemical personnel or literature is derived from experience and by no means should be taken as fact or construed as a recommendation to violate of any law, regulation or patent. It is the users responsibility to determine the suitability of any HB supplied material in their application. The individual conditions of each customer are well outside of our control and we cannot be held liable for its functionality and use. Please contact our office should you need specific information beyond what is supplied above. As with all Chemical usage safety precautions beyond the stated are highly recommended.

1665 ENTERPRISE PARKWAY, TWINSBURG, OH, 44087 Tel: (330) 920-8023 Fax: (330) 920-0971